

Filarc PZ6500

A copper coated, manganese-silicon alloyed rod for GTAW of all general engineering and structural steels with a minimum yield strength of max 420 MPa. The rod is usually welded with pure argon (I1) as the shielding gas.

Specifications	
Classifications	EN ISO 636-A : W 42 3 W3Si1 EN ISO 636-A : W3Si1 SFA/AWS A5.18 : ER70S-6
Approvals	CE : EN 13479 VdTÜV : 11842

Alloy Type	Carbon-manganese steel
-------------------	------------------------

Typical Tensile Properties			
Condition	Yield Strength	Tensile Strength	Elongation
EN Ar (I1)			
As Welded	470 MPa	560 MPa	26 %

Typical Charpy V-Notch Properties		
Condition	Testing Temperature	Impact Value
EN Ar (I1)		
As Welded	-30 °C	70 J

Typical Weld Metal Analysis %				
C	Mn	Si	S	P
Ar				
0.05	1.4	0.8	0.015	0.015

Typical Wire Composition %		
C	Mn	Si
0.078	1.46	0.85