### **Description**

Bare, corrosion-resistant, chromium-nickel-molybdenum rods for welding austenitic stainless alloys of the 18% Cr-8% Ni and 18% Cr-10% Ni-3% Mo types.

OK Tigrod 316L has good general corrosion resistance, particularly to corrosion in acid and chlorinated environments. The alloy has a low carbon content which makes it particularly recommended when there is a risk of intergranular corrosion. The alloy is widely used in the chemical and food-processing industries, as well as in shipbuilding and various types of architectual structure.

#### Welding current

DC(-)

# **Classifications**

SFA/AWS A5.9 ER316L EN 12072 W 19 12 3 L Werkstoffnummer ~1.4430

#### Wire composition

С	Si	Mn	Cr	Ni	Мо	Cu
< 0.03	0.5	1.8	19.0	12.5	2.8	<0.3

### Typical mech. properties all weld metal

Yield stress, MPa 470 Tensile strength, MPa 650 Elongation, % 32

### **Charpy V**

Test temps, °C Impact values, J

+20 140 -60 110 -196 70

#### **Approvals**

CL

DNV 316L (-60°C) Sepros UNA 485179 UDT DIN 8556

VdTÜV

## **Packing data**

Diameter, mm	Length, mm	Weight of rods/ box, kg
1.0	1000	5.0
1.2	1000	5.0
1.6	1000	5.0
2.0	1000	5.0
2.4	1000	5.0
3.2	1000	5.0
4.0	1000	5.0