

ER 80S-Ni2

Low Alloy WIRE/GTAW

Standards

EN/ISO-Standard - 636-A
EN/ISO-Classification - W 2Ni2

AWS-Standard - A5.28
AWS-Classification - ER 80S-Ni2

Features and Applications

- Copper coated, Ni-alloy (2,5% Ni), solid wire for low temperature, fine grained and austempering steels.
- Excellent impact toughness due to the addition of Nickel.
- Good mechanical properties at sub-zero temperatures down to -60°C.
- Especially suitable for use in the offshore industry.
- Typically used on the building up of cranes, transport, tanks, industrial facilities, equipment in general, pipelines, shipbuilding etc.
- Green wire is produced using virgin raw materials sourced from specialised steel mills, which ensures consistent reliability and quality.
- **Test Certificates can be found online @wilkinsonstar247.com**



Typical Base Materials

S235NL2, 14Ni6, 12Ni14, X12Ni5, S255N, S380N, S255NL, S380NL, S255NL1, S380NL1 ; A333: Gr. 1-3, A422: Gr.55-60, A334: Gr.3 ; 0Ni14, 13MnNi63, TTStE 355, TTStE 460, HY 80, TTStE 35 N*

* Illustrative, not exhaustive list

Welding Positions

EN ISO 6947 - PA, PB, PC, PD, PE, PF

Shielding Gases

EN ISO 14175 - TIG: I1 (Argon)

Polarity

DC (-)

Mechanical Properties (Typical)

Tensile Strength (N/mm ²)	Yield Strength (N/mm ²)	Elongation (%)	Impact Strength (J)	Test Temperature
630	530	26	100	-60°C

Mechanical properties are approximate and may vary based on the heat, shielding gas, welding parameters and other factors.

Chemical Composition % (Typical)

C %	Si %	Mn %	P %	S %	Cu % ^a	Cr %	Ni %	Mo %	Al %	V %	Zr+Ti %
0.08	0.50	1.10	<0.015	<0.015	<0.25	<0.15	2.50	<0.15	<0.020	<0.030	<0.050

^a (includes copper coating)

Packaging Data

Part No.	Diameter Ø (mm)	Package Length (mm)	Package Weight (Kg)	Package Type
6011100552	1.60	1000	5	Cardboard Tube
6011100553	2.40	1000	5	Cardboard Tube
6011100554	3.20	1000	5	Cardboard Tube

Liability: Whilst all reasonable efforts have been made to ensure the accuracy of the information contained, this information is subject to change without notice and can be only considered as suitable for general guidance.

