

## PRODUCT INFORMATION

### Silver Solder Flux

FO380022  
FO380050

#### SUMMARY

An active Silver Solder Flux with a working temperature range of 600-800 °C, designed for use with Sif Silver Solder alloys and SifCupron CuPAg alloys.

#### TARGET APPLICATIONS

Sif Silver Solder Flux can be used on most common metals capable of being brazed with silver brazing alloys melting up to 750 °C, including steels and coppers, and can be used to braze stainless steel at temperatures below 700 °C.



#### FURTHER INFORMATION

Ideal for hot-dipping of the brazing rod or for brush-on application as a paste, mixed with water.

#### ARTICLES & ACCESSORIES

Part Number	Product Description
FO380022	Silver Solder Flux 225g Jar
FO380050	Silver Solder Flux 500g Jar

#### TECHNICAL SPECIFICATION

Working Temperature °C	600-800
------------------------	---------

For further information, contact Weldability Sif technical support on **0870 330 7757** or email [service@weldability-sif.com](mailto:service@weldability-sif.com)



Registered in England No. 1684362  
Registered Office: as above

Doc Ref : WELDABILITY/PI/ FO380050