



# Product Data Sheet

W 'Tungsten inert gas arc welding'

# OK Tigrod 13.16

Signed by Mats Linde	Approved by Per Sundberg/Barbro Karlström	Reg no EN002912	Cancelling EN002284	Reg date 2005-05-16	Page 1 (1)
-------------------------	--	--------------------	------------------------	------------------------	---------------

## REASON FOR ISSUE

A new specification

## GENERAL

A copper coated, low-alloyed, chromium-molybdenum (1,3% Cr, 0,5% Mo), rod for GTAW of creep resistant steels like SA-387 Grade 11, A 335 Grade P11 or similar materials. OK Tigrod 13.16 is a high purity wire.

**Shielding Gas:** I1 (EN 439)

**Alloy Type:** Low alloyed steel (1,3%Cr, 0.5 % Mo)

## CLASSIFICATIONS Wire Electrode

SFA/AWS A5.28

ER80S-B2

## APPROVALS

Not applicable

## CHEMICAL COMPOSITION

	All Weld Metal (%)	Wire/Strip (%)	
	Nom	Min	Max
Ar			
C	0.08	0.07	0.12
Si	0.5	0.50	0.70
Mn	0.5	0.40	0.70
P	0.010		0.025
S	0.01		0.020
Cr	1.3	1.20	1.50
Mo	0.5	0.40	0.65
Cu	0.15		0.35
X			15
Others tot			0.50
Comments:		Comments: X = (10P+5Sb+4Sn+As)/100 (values in ppm)	

## MECHANICAL PROPERTIES OF WELD METAL

Properties	All Weld Metal	
	Min	Typ
	Ar (I1) AWS	
	Stress relieved 620°C 1h	
Rp0.2 (MPa)	470	640
Rm (MPa)	550	730
A4-A5 (%)	19	24
Charpy V at -40°C (J)		>47